

RECEIVED  
CENTRAL FAX CENTER

JAN 08 2009

PATENT APPLN. NO. 10/540,622  
RESPONSE UNDER 37 C.F.R. §1.111

PATENT  
NON-FINAL

IN THE CLAIMS:

1. (currently amended) A sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an electrical-loss material, the amount of said electrical-loss material in said sheet being 0.08 to 3 wt %.

2. (original) The sheet material for a radio wave absorber of claim 1, wherein the electrical-loss material is an electroconductive fiber.

3. (original) The sheet material for a radio wave absorber of claim 2, wherein the sheet is mixed paper including the electroconductive fiber.

4. (original) The sheet material for a radio wave absorber of claim 3, wherein a ratio ( $y/p$ ) of maximum electric conductivity ( $p$ ) of the mixed paper and electric conductivity ( $y$ ) measured in a direction orthogonal to a measurement direction presenting the maximum electric conductivity ( $p$ ) is in a range of 0.35 to 0.95.

PATENT APPLN. NO. 10/540,622  
RESPONSE UNDER 37 C.F.R. §1.111

PATENT  
NON-FINAL

5. (previously presented) The sheet material for a radio wave absorber of claim 1, wherein the paperboard structure is one selected from single faced paperboard, double faced paperboard, double wall paperboard and triple wall.

6. (previously presented) The sheet material for a radio wave absorber of claim 1, wherein thickness per a layer of the paperboard structure is 1 to 5 mm.

7. (previously presented) The sheet material for a radio wave absorber of claim 1, wherein the take up ratio of the corrugated medium to the liner of the paperboard structure is in a range of 1.2 to 2 times, and the interval between tops of adjacent corrugated mediums is in a range of 1 to 15 mm.

8. (currently amended) The sheet material for a radio wave absorber of claim 3, wherein the electroconductive fiber is a carbon fiber[[,]] and an average fiber length of the carbon fiber is 1 to 60 mm ~~and a mixing ratio in the mixed paper is 0.08 to 20 wt-%.~~

PATENT APPLN. NO. 10/540,622  
RESPONSE UNDER 37 C.F.R. §1.111

**PATENT  
NON-FINAL**

9. (original) The sheet material for a radio wave absorber of claim 8, wherein a content of sizing agent adhered to the carbon fiber is not more than 0.9 wt % of total carbon fiber weight.

10. (previously presented) The sheet material for a radio wave absorber of claim 1, wherein at least one selected from the group consisting of printing of colors, patterns or letters, and embossing of patterns or letters is applied to an outside surface of the liner.

11. (previously presented) A radio wave absorber, wherein the sheet material for a radio wave absorber of claim 1 is cut, folded, and assembled into a hollow three-dimensional structure body, which has a shape of wedge, polygonal pyramid, or polygonal cylinder.

12. (previously presented) A radio wave absorber, wherein, inside of the hollow three-dimensional structure body of claim 11, one or more of a sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an

PATENT APPLN. NO. 10/540,622  
RESPONSE UNDER 37 C.F.R. §1.111

PATENT  
NON-FINAL

electrical-loss material, is arranged parallel to a bottom surface of the radio wave absorber.

13. (previously presented) A radio wave absorber of which the hollow three-dimensional structure body of claim 11 has a pyramidal form, wherein a sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an electrical-loss material, is formed into an isosceles triangle plate two sides of which are along an inner wall of the radio wave absorber to match with each other at a right angle, and the other side of which is arranged perpendicularly to the bottom surface of the radio wave absorber.

14. (previously presented) A radio wave absorber of which the hollow three-dimensional structure body of claim 11 has a wedge form, wherein, inside of the radio wave absorber, a sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an electrical-loss material, is

PATENT APPLN. NO. 10/540,622  
RESPONSE UNDER 37 C.F.R. §1.111

PATENT  
NON-FINAL

formed into an isosceles triangle plate two sides of which are along an inner wall of the radio wave absorber to arrange one or more plates perpendicularly to a ridge line of wedge.

15. (previously presented) The radio wave absorber of claim 11, wherein a sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an electrical-loss material, has paired insert slits and insert flaps, and the hollow three-dimensional structure body is assembled by inserting the insert flap into the insert slits not to deform the shape.

16. (previously presented) The radio wave absorber of claim 11, wherein the hollow three-dimensional structure body is erected on a sintered ferrite plate.

17. (previously presented) The radio wave absorber of claim 11, wherein the hollow three-dimensional structure body is erected on a pedestal where a sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and

PATENT APPLN. NO. 10/540,622  
RESPONSE UNDER 37 C.F.R. §1.111

PATENT  
NON-FINAL

a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an electrical-loss material, is layered over in one or more layers.

18. (previously presented) The radio wave absorber of claim 11, wherein the pedestal is formed by layering on a reflective flat plate one or more sheet material layers for a sheet material for a radio wave absorber comprising a paperboard structure in which a corrugated medium and a planar liner are layered over each other, wherein the corrugated medium and/or the liner are constructed from a sheet including an electrical-loss material, where at least the corrugated medium is formed from a sheet including the electrical-loss material, and the hollow three-dimensional structure body is erected on the pedestal.

19. (previously presented) The radio wave absorber of claim 17, wherein two or more layers of the sheet material for a radio wave absorber are layered over so that a corrugated row direction of the corrugated medium crosses each other among the layers.